



BOARD DEFENSE®

Net Weight 25 LBS. (11.35kg)

TERMITICIDE, INSECTICIDE AND FUNGICIDE CONCENTRATE

For protection and treatment of Wood and Wood-Foam composite structural components, against decay fungi and wood-destroying insects, and cellulose insulation (paper-based) against decay fungi. Also controls such pests in infested wood.

DIRECTIONS:

For remedial control of organisms attacking wood, apply a 10% aqueous solution of BOARD DEFENSE® (1lb./gallon solution).

Solution may be applied by brush or spray until surface is thoroughly wetted (approximately 7-10 gallons per 1000 sq/ft.). For timbers 2 inches in thickness or greater, apply a second application 6 to 24 hours after the initial treatment. Application may also be made by drilling and then injecting the solution directly into the infested area. Inject a sufficient amount of solution to cause runoff from exit holes drilled into the infested member.

Alternatively, apply BOARD DEFENSE® dust to infested member by drill and injection directly into galleries or dust wood surfaces and wall voids at a rate of 2 to 3 pounds per 100 sq/ft.

PREPARATION OF SOLUTION: To prepare solution described above, water should be added to the tank about 80% of the final volume solution required. While agitating, 1.0 pound of BOARD DEFENSE® is then gradually added for each gallon of treating solution that is required. The remaining water is then added and the solution is agitated until the product has dissolved.

PRE-TREATMENT:

Wood, wood-foam composite structural components may be treated to prevent infestation of attacking organisms using the spray application method described above. For timbers 2 inches in thickness or greater apply a second application 6 to 24 hours after the first. Cellulose insulation may be treated to prevent infestation of attacking decay fungi by applying a 10% aqueous solution of BOARD DEFENSE® (1lb./gallon solution) by spraying surfaces uniformly during production or application (approximately one gallon per 500 pounds of cellulose insulation) Current Matrix Nutrition LLC specifications and test methods should be followed to ensure adequate chemical loading.

Manufactured By:
InCide Technologies, Inc.
50 N. 41st Ave
Phoenix, Az 85009
(602)233-0756

Distributed By:
Matrix Nutrition, LLC
4120 N. 38th Drive
Phoenix, Az 85019
(602)621-4944

EPA Reg. No. 44757-20 EPA Est. No. 44757-AZ

www.matrixnutritionllc.com

Made in USA
Refer to Material Data Sheet

KEEP OUT OF REACH OF CHILDREN

TAKE TIME



OBSERVE LABEL
DIRECTIONS